


# STONE

## TECHNICAL DATA

<p><b>TORRO</b> Andere benamingen: BALAK (Kavala)  Shiste  Origin :Aghia Eirini Marmari, (Greece)</p>	
---	---

### CARACTERISTICS - EUROPEAN STANDARD

	<b>Declares value</b>	
Flexural strength (EN 12372)	MPa	13.1
Flexural strength after 56 freeze/thaw cycles (EN12371 & EN12372)	Mpa	23.1
Abrasion resistance (EN14157- METHOD A)	mm	24.2
Apparent densisty (DIN 52102)	kg/m <sup>3</sup>	2718
Water absorption (DIN 52 102)	% vol	0,36
Compressive strength (DIN 52 105)	MPa	56,03

**USE: EXTERNAL PAVING (EN1341)**

STONE NV – Grote Steenweg 13, B-9870 Olsene – +32(09) 388 91 11 – [info@stone.be](mailto:info@stone.be) – [www.stone.be](http://www.stone.be)